

RYLARD

DISTRIBUTED BY: MAINLINE BUILDING PRODUCTS LIMITED • 2 SEFTON ROAD • LITHERLAND • LIVERPOOL • L21 7PG
TEL 0151 920 6451 • FAX 0151 920 6452 • EMAIL sales@rylardboats.com • WEB www.rylardboats.com

Reference: 04RCFWHI
Issue Number: 1
Issue Date: October 2009
Supersedes Issue: 0

RYLARD CEMENT FILLER (A799)

PRODUCT DESCRIPTION

A heavy duty filler for use on pitted or uneven surfaces to give an even surface for fine finishing. Cement filler is supplied in paste form and applied at high film thickness, which will not shrink or crack.

USES

For use with suitably primed Wood, Glass Fibre, Steel and Aluminium surfaces. It is a flexible filler ideal for screw or nail holes, bruises and seams above the waterline on timber craft and rivet heads giving a smooth surface before painting.

TECHNICAL PROPERTIES

Colour	White/Grey
Finish	Matt
Specific Gravity	2.6
Volume Solids	75%
Recommended Film Thickness	As required
Theoretical Spreading Rate	Will depend on film thickness
Application Method	Spatula
Flash Point	39°C
VOC	190g/Lt

Drying Times	20°C
Touch Dry	Will depend on film thickness
Hard Dry	Will depend on film thickness
Minimum Sanding Time	3 – 4 hours
Maximum Sanding Time	16 hours

This product can be stoved. But stoving must be carried out after minimum 16 hours curing. Typical schedule is 30 minutes at 120°C.

CERTIFICATION/APPROVALS

RECOMMENDED SYSTEMS All Rylard Primers and Finishes with the exception of Hull Coatings

SURFACE PREPARATION

Ensure surfaces are clean, dry and free from dirt, grease and other contamination. Degrease if necessary. The Cement Filler should be applied after coats of primer.

RYLARD

DISTRIBUTED BY: MAINLINE BUILDING PRODUCTS LIMITED • 2 SEFTON ROAD • LITHERLAND • LIVERPOOL • L21 7PG
TEL 0151 920 6451 • FAX 0151 920 6452 • EMAIL sales@rylardboats.com • WEB www.rylardboats.com

PRODUCT APPLICATION

Mixing	Stir well before use
Thinners	Thinner No.3 (only if required)
Application	Apply direct from the tin using a spatula and smooth evenly out. Cement Filler can be used to cover large areas using the “broad knife” technique when thinned with Thinner No.3
Cleaner	Thinner No.3
Cleanup Considerations	All equipment should be cleaned immediately after use with Thinner No.3 It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited.
The user must observe local health, safety and environmental regulations when using this product.
Consult Spencer Coatings Limited if there are any concerns over the suitability of this product.

PACK SIZES

750mls

PACK WEIGHTS

2kgs

STORAGE CONDITIONS

Store away from extremes of temperature. Shelf life 24 months in unopened containers. Ensure strict stock rotation is carried out.

LIMITATIONS

Not suitable for use in immersed conditions.
Do not apply when RH exceeds 88% or the surface is less than 2°C above dew point.
Drying will be affected in cold conditions.
Minimum application temperature 10°C.

DISCLAIMER

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using Spencer products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.